

# St Albans

**FIND OUT MORE ABOUT OUR BRICK RANGE**

T: 0161 641 3579

W: [www.manchesterbrick.com](http://www.manchesterbrick.com)



PRODUCT TECHNICAL INFORMATION	
MANCHESTER BRICK CODE	MBS01600
CONFIGURATION	Hand Form
COLOUR	Red with white and dark shades
APPEARANCE	Creased
SIZE	
Metric	65mm x 215mm x 102.5mm
PACK SIZE	544
INDIVIDUAL DRY BRICK WEIGHT	2.2kg

TECHNICAL PROPERTIES TO BS EN 771-1	
TYPE	Handmade
GROSS DRY DENSITY (KG/M <sup>3</sup> /TOLERANCE)	1,720kg/m <sup>3</sup> (D1)
COMPRESSIVE STRENGTH	>=20N/mm <sup>2</sup>
THERMAL CONDUCTIVITY*	←0.41 W/m.k
SIZE TOLERANCE (MEAN/RANGE)	T1/R1
WATER ABSORPTION	≤15% <sub>m</sub> /md
INITIAL RATE OF WATER ABSORPTION (KG/(M <sup>2</sup> MIN))	1.5–4.0kg/m <sup>2</sup> .min (IW3)
REACTION TO FIRE	A1
ACTIVE SOLUBLE SALTS	S2
DURABILITY DESIGNATION	F2



Technical data correct at time of issue. Individual dry brick weights can vary and are for guidance only. Any questions regarding this data should be referred to the Manchester Brick Technical Department. Due to the limitations of screen and print colour representation of product images it is advised that brick samples are viewed prior to ordering.

